



PCT / GB 00 / 023 05 #2

GB 00 / 023 05

INVESTOR IN PEOPLE

EJU

**PRIORITY  
DOCUMENT**  
SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH RULE 17.1(a) OR (b)

REC'D	17 JUL 2000
WIPO	PCT


The Patent Office  
Concept House  
Cardiff Road  
Newport  
South Wales  
NP10 8QQ

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.



Signed


Dated

30th June 2000

---

**THIS PAGE BLANK (USPTO)**

---



17JUN99 E455179-1 D01091  
F01/7700 0.00 - 9914023.8

The Patent Office

Cardiff Road  
Newport  
Gwent NP9 1RH

# Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

1. Your reference

PFC 1442 GB

2. Patent application number

(The Patent Office will fill in this part)

9914023.8

3. Full name, address and postcode of the or of each applicant (underline all surnames)

JOHNSON MATTHEY PUBLIC LIMITED COMPANY

2-4 COCKSPUR STREET  
TRAFALGAR SQUARE  
LONDON SW1Y 5BQ

Patents ADP number (if you know it)

If the applicant is a corporate body, give the country/state of its incorporation

GB

536268007

4. Title of the invention

GAS DIFFUSION SUBSTRATE AND ELECTRODE

5. Name of your agent (if you have one)

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

IAN CARMICHAEL WISHART

JOHNSON MATTHEY TECHNOLOGY CENTRE  
BLOUNTS COURT  
SONNING COMMON  
READING RG4 9NH

Patents ADP number (if you know it)

7258312601

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number  
(if you know it)

Date of filing  
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing  
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

YES

- a) any applicant named in part 3 is not an inventor, or
- b) there is an inventor who is not named as an applicant, or
- c) any named applicant is a corporate body.

See note (d))

# Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form.  
Do not count copies of the same document

Continuation sheets of this form	0
Description	10
Claim(s)	3
Abstract	1
Drawing(s)	1

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (*Patents Form 7/77*)

Request for preliminary examination and search (*Patents Form 9/77*) ONE

Request for substantive examination (*Patents Form 10/77*)

Any other documents  
(please specify)

11. I/We request the grant of a patent on the basis of this application.

Signature

*J E Swift*

Date 16/6/99

J E SWIFT

12. Name and daytime telephone number of person to contact in the United Kingdom

MRS F E STRANGE 0118 924 2125

## Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

## Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

GAS DIFFUSION SUBSTRATE AND ELECTRODE

The present invention relates to an improved electrically conducting gas diffusion substrate and electrode comprising said substrate, suitable for use in particular in proton exchange membrane fuel cells. The invention further relates to a membrane electrode assembly and fuel cell comprising said substrate or electrode.

Electrochemical cells invariably comprise at their fundamental level a solid or liquid electrolyte and two electrodes, the anode and cathode, at which the desired electrochemical reactions take place. A fuel cell is an energy conversion device that efficiently converts the stored energy of its fuel into electrical energy by combining hydrogen, stored as a gas, or methanol, stored as a liquid or gas, with oxygen to generate electrical power. The hydrogen or methanol is oxidised at the anode and oxygen reduced at the cathode. In these cells gaseous reactants and/or products have to be diffused into and/or out of the cell electrode structures. The electrodes therefore are specifically designed to be porous to gas diffusion in order to optimise the contact between the reactants and the reaction sites in the electrode to maximise the reaction rate. An electrolyte is required which is in contact with both electrodes and which may be alkaline or acidic, liquid or solid. In a solid polymer fuel cell (SPFC), also known as a proton-exchange membrane fuel cell (PEMFCs), the electrolyte is a solid proton-conducting polymer membrane, commonly based on perfluorosulphonic acid materials. These electrolytes must be maintained in a hydrated form during operation in order to prevent loss of ionic conduction through the electrolyte; this limits the operating temperature of the PEMFC to between 70°C and 120°C, depending on the operating pressure. The PEMFC does, however, provide much higher power density output than the other fuel cell types, and can operate efficiently at much lower temperatures. Because of this, it is envisaged that the PEMFC will find use in vehicular power generation and small-scale residential power generation applications. In particular, vehicle zero-emission regulations have been passed in areas of the United States that are likely to restrict the use of the combustion engine in the future. Pre-commercial PEMFC-powered buses and prototype PEMFC-powered vehicles are now being demonstrated for these applications.

Due to the relatively low operating temperatures of these systems, the oxidation and reduction reactions require the use of catalysts in order to proceed at useful rates. Catalysts, which promote the rates of electrochemical reactions, such as oxygen reduction and hydrogen oxidation in a fuel cell, are often referred to as electrocatalysts. Precious metals, in particular platinum, have been found to be the most efficient and stable electrocatalysts for all low-temperature fuel cells operating below 300°C. The platinum electrocatalyst is provided as very small particles (~20-50Å) of high surface area, which are often, but not always, distributed on and supported by larger macroscopic conducting carbon particles to provide a desired catalyst loading. Conducting carbons are the preferred materials to support the catalyst.

In the PEMFC the combined laminate structure formed from the membrane and the two electrodes is known as a membrane electrode assembly (MEA). The MEA will typically comprise several layers, but can in general be considered, at its basic level, to have five layers, which are defined principally by their function. On either side of the membrane an anode and cathode electrocatalyst is incorporated to increase the rates of the desired electrode reactions. In contact with the electrocatalyst containing layers, on the opposite face to that in contact with the membrane, are the anode and cathode gas diffusion substrate layers. The anode gas diffusion substrate is designed to be porous and to allow the reactant hydrogen or methanol to enter from the face of the substrate exposed to the reactant fuel supply, and then to diffuse through the thickness of the substrate to the layer which contains the electrocatalyst, usually platinum metal based, to maximise the electrochemical oxidation of hydrogen or methanol. The anode electrocatalyst layer is also designed to comprise some level of the proton conducting electrolyte in contact with the same electrocatalyst reaction sites. With acidic electrolyte types the product of the anode reaction are protons and these can then be efficiently transported from the anode reaction sites through the electrolyte to the cathode layers. The cathode is also designed to be porous and to allow oxygen or air to enter the substrate and diffuse through to the electrocatalyst layer reaction sites. The cathode electrocatalyst combines the protons with oxygen to produce water. Product water then has to diffuse out of the cathode structure. The structure of the cathode has to be designed such that it enables the efficient removal of the product water. If water builds up in the cathode, it becomes more difficult for the

reactant oxygen to diffuse to the reaction sites, and thus the performance of the fuel cell decreases. In the case of methanol fuelled PEMFCs, additional water is present due to the water contained in the methanol, which can be transported through the membrane from the anode to the cathode side. The increased quantity of water at the cathode requires  
5 removal. However, it is also the case with proton exchange membrane electrolytes, that if too much water is removed from the cathode structure, the membrane can dry out and the performance of the fuel cell also decreases.

The complete MEA can be constructed by several methods. The electrocatalyst  
10 layers can be bonded to one surface of the gas diffusion substrates to form what is known as a gas diffusion electrode. The MEA is then formed by combining two gas diffusion electrodes with the solid proton-conducting membrane. Alternatively, the MEA may be formed from two porous gas diffusion substrates and a solid proton-conducting polymer membrane catalysed on both sides; or indeed the MEA may be formed from one gas  
15 diffusion electrode and one gas diffusion substrate and a solid proton-conducting polymer catalysed on the side facing the gas diffusion substrate.

Gas diffusion substrates or electrodes are employed in many different electrochemical devices in addition to fuel cells, including metal-air batteries,  
20 electrochemical gas sensors, and electrochemical reactors for the electrosynthesis of useful chemical compounds.


In most practical fuel cell systems, the hydrogen fuel is produced by converting a hydrocarbon-based fuel (such as methane) or an oxygenated hydrocarbon fuel (such as  
25 methanol) to hydrogen in a process known as reforming. This fuel, referred to as reformat, contains (in addition to hydrogen) high levels of carbon dioxide ( $\text{CO}_2$ ), of around 25%, and small amounts of impurities such as carbon monoxide (CO), typically at levels of around 1%. For fuel cells operating at temperatures below  $200^\circ\text{C}$ , and especially for the PEMFC operating at temperatures around  $100^\circ\text{C}$ , it is well known that CO, even at  
30 levels of 1-10ppm, is a severe poison for the platinum electrocatalysts present in the electrodes. This leads to a significant reduction in fuel cell performance, *i.e.* the cell voltage at a given current density is reduced. This deleterious effect is more pronounced in

PEMFCs operating at lower temperatures.

Various methods have been employed to alleviate anode CO poisoning. For example, reformer technology has been redesigned to include an additional catalytic reactor, known as a preferential or selective oxidation reactor. This involves the injection of air or oxygen into the hydrogen-containing reactant gas stream, prior to it passing over a selective oxidation catalyst, to oxidise the CO to CO<sub>2</sub>. This can reduce the levels of CO from 1-2% down to below 100ppm. However, even at these levels, the anode electrocatalyst in the PEMFC is still poisoned.

A further method to alleviate CO poisoning is to use an electrocatalyst that itself has a degree of tolerance to CO, for example Pt/Ru as described by Niedrach *et al* in *Electrochem. Technol.*, 5, 318, (1967). However, again, it is not possible to fully attain the performance observed when using pure hydrogen *i.e.* in the absence of CO in the fuel stream, using this approach in isolation.

It has also been found that poisoning of the electrocatalyst by CO at levels of 1-100ppm can be reduced by the use of an oxygen or air bleed directly into the anode gas stream just before it enters the anode chamber of the fuel cell itself. This is described by Gottesfeld and Pafford in *J. Electrochem. Soc.*, 135, 2651 *et seq* (1988). This technique is believed to have the effect of oxidising the residual CO in the fuel to CO<sub>2</sub>, the reaction being catalysed by electrocatalyst sites present in the anode:



This technique provides fuel cell performance that is much closer to the performance observed when no CO is present in the fuel stream.

An improved structure in combination with the use of an air bleed is to add to the substrate a second catalyst (a "gas phase catalyst") that will oxidise CO in the presence of hydrogen, for example as described in European Patent 0736921. The use of the additional gas phase catalyst gives improved performance of the electrode over the corresponding



electrode without a gas phase catalyst. However, if the gas phase catalyst is supported on a conducting carbon support as described in EP 0736921, it may not be possible to isolate the gas phase catalyst from the overall electrode potential. The presence of oxygen on the gas phase catalyst particles will induce the gas phase catalyst potential to tend towards a more oxidising, i.e. higher, potential. Overall the electrode could then exhibit a mixed cell potential higher than the hydrogen oxidation potential, leading to a loss of electrode efficiency. Likewise, the electronic conductivity can also lead to a pinning of the potential of the selective oxidation catalyst to the low potential of the anode, which is close to the hydrogen oxidation potential. This will affect the ability of the selective oxidation catalyst to oxidise CO even in the presence of oxygen.

The use of a gas phase catalyst still requires the presence of an air bleed and there are concerns over the long-term sustainability of the cell performance when this approach is employed. This is particularly the case if high levels of air bleed, equivalent to 4% and above of the total reformat fuel volume, are required.

The object of the present invention is to provide an electrically conducting gas diffusion substrate and electrode capable of removing oxidisable impurities from a gas stream, in which the gas phase catalyst is unable to participate in the electrochemical reaction. This allows optimum performance for both the gas phase catalyst and the electrocatalyst in the electrode because catalyst potentials are then independent of each other. Thus, either a lower level of air bleed is required to give the same performance, or using conventional levels of air bleed, a higher performance is obtained.

Accordingly, the present invention provides an electrically conducting gas diffusion substrate comprising an electrically conducting porous structure and a first catalytic component, characterised in that the first catalytic component comprises a first catalyst supported on an electrically non-conducting support.

The electrically conducting porous structure may be a woven or non-woven fibrous material. For example, the porous structure may be a rigid carbon fibre paper, such as the TGP Series produced by Toray Industries; a woven carbon cloth, such as PWB-3

produced by Zoltek; or a non-woven carbon fibre structure, such as Optimat 203 produced by Technical Fibre Products. Alternatively, the porous structure may be formed from a polymer; for example an expanded polymer mesh as described in WO98/27606. Alternatively, the porous structure may be a metal mesh, for example of nickel or steel.

5 The electrical conductivity of the porous structure may be improved by the addition of a filler material. Suitably, the filler material comprises a particulate carbon and a polymer, the carbon suitably being in the form of a powder. The carbon powder may be any of the materials generally designated as carbon black such as acetylene blacks, furnace blacks, pitch coke based powders and graphitised versions of such materials. Suitably also both  
10 natural and synthetic graphites may be used in this application. Such materials may be used either alone or in combination. The particulate carbon, or carbons, in the fill are held together by one or more polymers. The polymeric materials used will contribute to the essential electrode structural properties such as pore size distribution, hydrophobic/hydrophilic balance and physical strength of the gas diffusion layer.  
15 Examples of such polymers include polytetrafluoroethylene (PTFE), fluorinated ethylene-propylene (FEP), polyvinylidene difluoride (PVDF), Viton A, polyethylene, polypropylene, ethylene-propylene. The preferred final polymer is PTFE or FEP. The filler material is suitably embedded within the porous structure.

20 Suitably, the first catalyst is a gas-phase catalyst designed to remove contaminant gases in the fuel or oxidant feed streams, such as for example carbon monoxide in the hydrogen fuel when this is supplied from a reformer. Suitably, the first catalyst may be a noble metal, for example platinum, palladium, ruthenium or rhodium, or a non-noble metal, for example chromium, molybdenum, nickel or manganese, or a combination of one  
25 or more noble metals and/or non-noble metals. The first catalyst is supported on an electrically non-conducting support, which is suitably an oxidic support such as alumina, silica, ceria or zirconia.

The first catalytic component may either be embedded within the porous structure  
30 or may be applied to the porous structure as a surface layer. If applied to the porous structure as a surface layer, the first catalytic component is suitably applied as a mixture with electrically conducting particles, for example carbon particles such as carbon black. If

the first catalytic component is embedded within the porous structure, the first catalytic component may optionally be mixed with electrically conducting particles.

5 The electrically conducting gas diffusion substrate of the invention may be prepared by taking a pre-formed porous structure, with or without the addition of a filler material, and subsequently in-filling with the first catalytic component or by applying the first catalytic component as a surface layer. If the first catalytic component is embedded within the porous structure, the majority of the catalytic component will be forced into the structure of the porous structure, although a small quantity may remain on the surface. The 10 first catalytic component may be embedded within the porous structure by conventional methods known in the art, for example as filtration, powder vacuum deposition, spray deposition, electrodeposition, extrusion, printing, rolling, K-bar, doctor blade methods, or thin-film casting. If the first catalytic component is applied to the surface of the electrically conducting porous structure, optionally mixed with electrically conducting particles, this 15 too may be carried out using conventional methods known in the art, for example as filtration, powder vacuum deposition, spray deposition, electrodeposition, extrusion, printing, rolling, K-bar, doctor blade methods, or thin-film casting.

Alternatively, in the case of a non-woven fibre structure being used, the gas 20 diffusion substrate may be prepared in a single step process by adapting a continuous manufacturing technique, for example paper making, or extrusion or pultrusion.

A second aspect of the present invention provides a gas diffusion electrode comprising an electrically conducting gas diffusion substrate as hereinbefore defined and a 25 second catalytic component.

Preferably, the second catalytic component comprises an electrocatalyst which facilitates the electrochemical reaction, and may be, for example, a precious metal or a transition metal as the metal or metal oxide, either unsupported or supported in a dispersed 30 form on a carbon support; an organic complex, in the form of a high surface area finely divided powder or fibre; or a combination of these options. Most suitably, the second catalytic component is a platinum/ruthenium alloy supported on carbon black or platinum

supported on carbon black.

When functioning as a gas diffusion electrode, the first catalytic component is unable to partake in the electrochemical reaction since the first catalyst is supported on an electrically non-conducting support, and thus no mixed cell potential is obtained.

The electrode of the invention may be used either as the anode or the cathode; suitably it is used as the anode and the first catalytic component is selected to remove CO from an impure hydrogen feed. If used as a cathode, the first catalytic component is selected to remove any oxidisable impurities, whether airborne or unreacted fuels crossing over from the anode.

The second catalytic component may either be applied to the gas diffusion substrate as a separate layer, the first catalytic component either being embedded within the porous structure or applied as a surface layer. Alternatively, the second catalytic component may be applied to the porous structure as a surface layer mixed with the first catalytic component. If the first and second catalytic components are mixed prior to application to the porous substrate, there may or may not be an additional electrically conducting substance included in the mixed layer, since this property will be provided by second catalytic component.

The second catalytic component, whether applied separately or mixed with the first catalytic component may be applied to the gas diffusion substrate or porous structure by conventional methods known in the art, for example by filtration, powder vacuum deposition, spray deposition, electrodeposition, extrusion, printing, rolling, K-bar, doctor blade methods, or thin-film casting.

A third aspect of the invention provides a membrane electrode assembly comprising a gas diffusion electrode of the invention as hereinbefore defined and a second gas diffusion electrode which may or may not be an electrode according to the invention, and a solid polymer membrane, for example Nafion®. Alternatively, the invention provides a membrane electrode assembly comprising a gas diffusion electrode of the invention as

hereinbefore defined, a gas diffusion substrate which may or may not be a substrate according to the invention and a solid polymer membrane, for example Nafion<sup>®</sup>, wherein an electrocatalyst layer is applied to the side of the membrane facing the gas diffusion substrate. Alternatively, the invention provides a membrane electrode assembly comprising a gas diffusion substrate of the invention as hereinbefore defined, a gas diffusion electrode which may or may not be an electrode according to the invention and a solid polymer membrane, for example Nafion<sup>®</sup>, wherein an electrocatalyst layer is applied to the side of the membrane facing the gas diffusion substrate. Alternatively, the invention provides a membrane electrode assembly comprising a gas diffusion substrate of the invention as hereinbefore defined and a second gas diffusion substrate which may or may not be a substrate according to the invention, and a solid polymer membrane, for example Nafion<sup>®</sup>, wherein an electrocatalyst layer is applied to both sides of the solid polymer membrane.

A still further aspect of the invention provides a fuel cell comprising a gas diffusion substrate according to the present invention. A yet further aspect provides a fuel cell comprising a gas diffusion electrode according to the present invention. A yet further aspect provides a fuel cell comprising a membrane electrode assembly according to the present invention.

The invention will now be further described with reference to the following examples.

#### COMPARATIVE EXAMPLE 1 – Pt(Pt/Ru)

A fuel cell anode was prepared as described in Example 1 of EP 0 736 921 with a gas phase catalyst layer prepared from 20wt%Pt catalyst supported on Shawinigan carbon, to give a platinum loading of 0.2 mgcm<sup>-2</sup> of Pt, and a platinum/ruthenium electrocatalyst with metal loadings of 0.27 mgcm<sup>-2</sup> of Pt and 0.14 mgcm<sup>-2</sup> of Ru.

#### EXAMPLE 1 - (Rh/Alumina)/(Pt/Ru)

A catalyst containing rhodium supported on alumina, such that the nominal

rhodium loading is 5 wt%, was purchased from Johnson Matthey Alfa (Type 524, nominal surface area  $141\text{m}^2\text{g}^{-1}$ ). A PTFE containing ink (35 wt% solids w.r.t. catalyst weight) was prepared from the alumina-supported rhodium catalyst by a method similar to that described in EP 0 736 921. A layer of the rhodium ink was applied to a first side of a pre-  
5   teflonated Toray TPG90 paper to give a Rh loading of  $0.12\text{ mgcm}^{-2}$ , such that the rhodium ink was embedded within the Toray paper, thus enabling electronic conductivity through the substrate. The electrocatalyst ink was prepared comprising a PtRu alloy catalyst at nominal loadings of 20 wt%Pt and 10 wt% Ru loading supported on Cabot Vulcan XC72R by a similar method to that described in Comparative Example 1. The electrocatalyst ink  
10   was applied to the second side of the Toray paper substrate at a loading of  $0.29\text{ mgcm}^{-2}$  of Pt and  $0.15\text{ mgcm}^{-2}$  of Ru.

### SAMPLE EVALUATION

15       From the anodes prepared as detailed in Comparative Example 1 and Example 1, two membrane electrode assemblies were prepared using Nafion 115 membranes and conventional cathodes with nominal Pt loadings of  $0.75\text{ mgcm}^{-2}$ . The MEA was prepared by hot-pressing the membrane between the anode and the cathode. Samples were then conditioned in single cells overnight and the performance in synthetic reformat of the  
20   composition 100 ppm CO/Hydrogen was recorded. Figures 1 and 2 show the performance data for the MEAs of Example 1 and Comparative Example 1 respectively. Initially, the performance on pure hydrogen and air (at the cathode) is recorded. After several minutes, the anode gas stream is switched to 100ppm/hydrogen which causes a degradation of the cell voltage by approximately 220 mV for Example 1 and 200 mV for Comparative  
25   Example 1. After the performance has stabilised, air bleeds of increasing levels, starting at 1%, are applied. Example 1 shows slow recovery of the performance loss but almost perfect recovery at 2% air bleed. Comparative Example 1 exhibits a performance still 80 mV lower than that with pure hydrogen at air bleed levels of up to 2%. Only at 5% air bleed level near-complete recovery is observed.

CLAIMS

1. An electrically conducting gas diffusion substrate comprising an electrically conducting porous structure and a first catalytic component, characterised in that the first  
5 catalytic component comprises a first catalyst supported on an electrically non-conducting support.
2. A gas diffusion substrate according to claim 1 wherein the first catalyst is a gas-phase catalyst.
- 10 3. A gas diffusion substrate according to claim 1 or claims 2 wherein the first catalyst is one or more noble metals or non-noble metals or a combination thereof.
4. A gas diffusion substrate according to any preceding claim wherein the first  
15 catalyst is one or more metals selected from the group consisting of platinum, palladium, ruthenium, rhodium, chromium, molybdenum, nickel and manganese or a combination thereof.
5. A gas diffusion substrate according to any preceding claim wherein the  
20 electrically non-conducting support is an oxidic support.
6. A gas diffusion substrate according to claim 5 wherein the oxidic support is alumina, silica, ceria or zirconia.
- 25 7. A gas diffusion substrate according to any preceding claim, wherein the porous structure is a woven or non-woven fibrous material.
8. A gas diffusion substrate according to any one of claims 1 to 6, wherein the porous structure is formed from a polymer.
- 30 9. A gas diffusion substrate according to any one of claims 1 to 6, wherein the porous structure is a metal mesh.

10. A gas diffusion substrate according to any one of claims 7, 8 and 9 wherein the porous structure further comprises a filler material.

11. A gas diffusion substrate according to any preceding claim wherein the first catalytic component is embedded within the porous structure.

12. A gas diffusion substrate according to any one of claims 1 to 10 wherein the first catalytic component is applied to the porous structure as a surface layer.

10 13. A gas diffusion substrate according to claim 12 wherein the first catalytic component is mixed with electrically conducting particles.

14. A process for the preparation of a gas diffusion substrate according to any preceding claim, said process comprising in-filling a pre-formed porous structure with the first catalytic component or applying the first catalytic component to the surface of a pre-formed porous structure.

15. A gas diffusion electrode comprising an electrically conducting gas diffusion substrate as claimed in any one of claims 1 to 13 and a second catalytic component.

20

16. A gas diffusion electrode according to claim 15 wherein the second catalytic component comprises an electrocatalyst.

17. A gas diffusion electrode according to claim 15 or claim 16 wherein the second catalytic component is a precious metal or a transition metal as the metal or metal oxide, either unsupported or supported in a dispersed form on a carbon support; a carbon or an organic complex, in the form of a high surface area finely divided powder or fibre, or a combination of thereof.

25 18. A gas diffusion electrode according to claim 17, wherein the second catalytic component is a platinum/ruthenium alloy supported on carbon black or platinum supported on carbon black.



19. A membrane electrode assembly comprising a gas diffusion electrode as claimed in any one of claims 15 to 18 and a second gas diffusion electrode which may or may not be an electrode as claimed in any one of claims 15 to 18, and a solid polymer membrane.

5

20. A membrane electrode assembly comprising a gas diffusion electrode as claimed in any one of claims 15 to 18, a gas diffusion substrate which may or may not be a substrate as claimed in any one of claims 1 to 13 and a solid polymer membrane, wherein an electrocatalyst layer is applied to the side of the membrane facing the gas diffusion substrate.

10

21. A membrane electrode assembly comprising a gas diffusion substrate as claimed in any one of claims 1 to 13, a gas diffusion electrode which may or may not be an electrode as claimed in any one of claims 15 to 18 and a solid polymer membrane, wherein an electrocatalyst layer is applied to the side of the membrane facing the gas diffusion substrate.

15

22. A membrane electrode assembly comprising a gas diffusion substrate as claimed in any one of claims 1 to 13, and a second gas diffusion substrate which may or may not be a substrate as claimed in any one of claims 1 to 13, and a solid polymer membrane, wherein an electrocatalyst layer is applied to both sides of the solid polymer membrane.

20

23. A fuel cell comprising a gas diffusion substrate as claimed in any one of claims 1 to 13.

25

24. A fuel cell comprising a gas diffusion electrode as claimed in any one of claims 15 to 18.

25. A fuel cell comprising a membrane electrode assembly as claimed in any one of claims 19 to 22.

30


---

**Abstract of the Invention**


**GAS DIFFUSION SUBSTRATE AND ELECTRODE**

An electrically conducting gas diffusion substrate, capable of removing oxidisable impurities from an impure gas stream, which comprises an electrically conducting porous structure and a first catalytic component, wherein the first catalytic component comprises a first catalyst supported on an electrically non-conducting support is disclosed. In addition, an electrode, a membrane electrode assembly and a fuel cell each comprising said electrically conducting gas diffusion substrate is disclosed.

---

**Figure 1**

5

**Figure 2**

PCT/GP

0370230E

23/77 Aled 14-6-2000

Johnson Matthey Tech Cen 2

**THIS PAGE BLANK** (USPTO)